

# Associated Paint, Inc.



## 41-600.01

### Acrylic Masonry Sealer White Data Sheet

<u>Characteristics:</u>	<u>Specifications</u>	<u>Surface Preparation</u>
<p><i>Also Available as 41-500A Clear</i></p> <p>Acrylic Masonry Sealer is a waterborne penetrating sealer formulated to bind loose and powdery chalk. Acrylic Sealer dries to a smooth, uniform finish that provides a sound repaintable surface. Acrylic Sealer may also be used on new masonry and concrete surfaces as a prime coat to seal the surface and block efflorescence. Acrylic Masonry Sealer is also available as 41-500A clear.</p> <p><b>Vehicle Type:</b> 100% Acrylic</p> <p><b>FINISH:</b> Low Sheen</p> <p><b>RECOMMENDED USES:</b></p> <ul style="list-style-type: none"> <li>• Concrete</li> <li>• Metal</li> <li>• Masonry Surfaces</li> <li>• Primed Wood</li> </ul> <p><b>TINTING:</b> White may be tinted to light and medium tints with universal colorants.</p> <p><b>THINNING:</b> Not recommended.</p> <p><b>DRYING TIME, @ 77° F, 50% RH:</b> Temperature &amp; Humidity Dependent</p> <p><b>Touch:</b> 1 Hour <b>Recoat:</b> 2 to 3 hours <b>Flash Point:</b> N/A</p> <p><b>VOC:</b> &lt; 100 g/l</p> <p><b>Weight Solids:</b> 36.5 ± 2% <b>Volume Solids:</b> 25.6 ± 2% <b>Weight Per Gallon:</b> 9.7 Lbs</p>	<p><b>COVERAGE:</b> 41-600 will cover up to 250 sq.ft @ 4.0 mils wet, 1.3 mils dry</p> <p><b>APPLICATION:</b> Apply 41-600 by brush, roller or airless spray (1800-2000PSI and .017 tip).</p> <p><b>Cleanup Information</b></p> <p>Clean spills and spatters immediately with soap and warm water. Clean hands and tools immediately after use with soap and warm water. After cleaning, flush spray equipment with mineral spirits to prevent rusting of the equipment. Follow manufacturer's safety recommendations when using mineral sprits.</p> <p><b>Surface Preparation</b></p> <p><b>Warning!</b> Removal of old paint by sanding, scraping or other means may generate dust or fumes that contain lead. Exposure to lead dust or fumes may cause brain damage or other adverse affects, especially in children or pregnant women. Controlling exposure to lead or other hazardous substances requires the use of proper protective equipment, such as a properly fitted respirator (NIOSH approved) and proper containment and cleanup. For more information, call the National Lead Information Center at 1-800-424-LEAD (in US) or contact your local health authority.</p>	<p><b>Masonry, Concrete, Cement, Block</b> All new surfaces must be cured according to the supplier's recommendations usually about 30 days. Remove all form release and curing agents. Rough surfaces can be filled to provide a smooth surface. If painting cannot wait 30 days, allow the surface to cure 7 days and prime the surface with <b>(41-600TG Hot Stucco Masonry Primer, 40-500 or 40-540)</b>.</p> <p><b>Wood</b> Sand any exposed wood to a fresh surface. Patch all holes and imperfections with a wood filler or putty and sand smooth.</p> <p><b>Mildew</b> Remove before painting by washing with a solution of 1 part liquid bleach and 3 parts water. Apply the solution and scrub the mildewed area. Allow the solution to remain on the mildewed area for 10 minutes. Rinse thoroughly with water and allow the surface to dry prior to painting. Wear protective eyewear, waterproof gloves, and protective clothing. Quickly wash off any mixture that comes in contact with your skin. Do not add detergents or ammonia to the bleach water solution.</p>