

# Associated Paint, Inc.



## 41-600TG.01

### Acrylic Masonry Hot Stucco Primer/Filler Sealer Data Sheet

<u>Characteristics:</u>	<u>Specifications</u>	<u>Surface Preparation</u>
<p>Acrylic Masonry Filler-Sealer is a water-borne coating formulated to handle a pH level of 12 or lower prior to application. Use on properly prepared concrete and masonry surfaces. Dries to a smooth, uniform finish that provides a sound paintable surface.</p> <ul style="list-style-type: none"> <li>• Excellent adhesion</li> <li>• Resists alkali and efflorescence.</li> <li>• Resists moisture vapor</li> <li>• Resists peeling, blistering, and cracking</li> </ul> <p><b>Vehicle Type:</b> 100% Acrylic</p> <p><b>FINISH:</b> Flat</p> <p><b>RECOMMENDED USES:</b></p> <ul style="list-style-type: none"> <li>• Concrete</li> <li>• Masonry Surfaces</li> </ul> <p><b>TINTING:</b> White may be tinted to light colors with up to 2 oz. per gallon of universal colorant.</p> <p><b>THINNING:</b> Not recommended.</p> <p><b>DRYING TIME, @ 77° F, 50% RH:</b> Temperature &amp; Humidity Dependent</p> <p><b>Touch:</b> 1 Hour <b>Recoat:</b> 4 hours <b>Flash Point:</b> N/A</p> <p><b>VOC:</b> &lt; 100 g/l</p> <p><b>Weight Solids:</b> 53 ± 2% <b>Volume Solids:</b> 36 ± 2% <b>Weight Per Gallon:</b> 11 Lbs</p>	<p><b>Coverage:</b> 41-600TG will cover up to 175 -185 sq.ft @ 4.5 mils wet.</p> <p><b>Application:</b> Apply 41-600 by brush, roller or airless spray (1800-2400PSI and .017 tip).</p> <p><b>Limitations:</b> Coatings have a greater resistance against failure when applied to a surface with a lower alkaline level below 8.5. Do not apply when hydrostatic pressure is expected, where water intrusion may occur, or on surfaces in constant contact with moisture.</p> <p><b>Cleanup Information</b></p> <p>Clean spills and spatters immediately with soap and warm water. Clean hands and tools immediately after use with soap and warm water. After cleaning, flush spray equipment with mineral spirits to prevent rusting of the equipment. Follow manufacturer's safety recommendations when using mineral spirits.</p> <p><b>Surface Preparation</b></p> <p><b>Warning!</b> Removal of old paint by sanding, scraping or other means may generate dust or fumes that contain lead. Exposure to lead dust or fumes may cause brain damage or other adverse affects, especially in children or pregnant women. Controlling exposure to lead or other hazardous substances requires the use of proper protective equipment, such as a properly fitted respirator (NIOSH approved) and proper containment and cleanup. For more information, call the National Lead Information Center at 1-800-424-LEAD (in US) or contact your local health authority.</p>	<p><b>Masonry, Concrete, Cement, Block</b> All new surfaces must be cured according to the supplier's recommendations usually about 30 days. Remove all form release and curing agents. Rough surfaces can be filled to provide a smooth surface. If painting cannot wait 30 days, allow the surface to cure 7 days and prime the surface with <b>(41-600TG Hot Stucco Masonry Primer, 40-500 or 40-540)</b>.</p> <p><b>Mildew</b> Remove before painting by washing with a solution of 1 part liquid bleach and 3 parts water. Apply the solution and scrub the mildewed area. Allow the solution to remain on the mildewed area for 10 minutes. Rinse thoroughly with water and allow the surface to dry prior to painting. Wear protective eyewear, waterproof gloves, and protective clothing. Quickly wash off any mixture that comes in contact with your skin. Do not add detergents or ammonia to the bleach water solution.</p>