

Associated Paint, Inc.



65-521.01

Acrylic Latex Traffic Paint

65-521 White, 65-531 Yellow, 65-541 Handicap Blue

Data Sheet

<p style="text-align: center;"><u>Characteristics:</u></p> <p>Acrylic Latex Traffic Paint is designed for use over bituminous and concrete surfaces. Traffic Paint goes on easily and dries quickly to a durable coating that resists weather, oil, grease and heavy traffic. Available in all standard traffic marking colors including lead-free yellow.</p> <p>Vehicle Type: Acrylic - Latex</p> <p>FINISH: Flat</p> <p>RECOMMENDED USES:</p> <ul style="list-style-type: none"> • Highway Lines • Roadway Lines • Tennis Courts • Parking Lots • Airfields • Factory Floors • Concrete Bumpers <p>TINTING: None</p> <p>THINNING: Not recommended., however for spray application add no more than 1/2 a pint of water per gallon of Traffic Paint.</p> <p style="text-align: center;"><u>Specifications</u></p> <p>DRYING TIME, @ 77° F, 50% RH: Temperature & Humidity Dependent</p> <p>Touch: 45 minutes Recoat: 2 hours Flash Point: N/A</p> <p>VOC: <100 g/l</p> <p>Weight Solids: 47 % ± 2% Volume Solids: 32 % ± 2% Weight Per Gallon: 10.9 Lbs</p>	<p style="text-align: center;"><u>Surface Preparation</u></p> <p>COVERAGE: Acrylic Latex Traffic Paint will cover up to 400 sq.ft per gallon @ 4.0 mils wet, 1.5 mils dry.</p> <p>APPLICATION: Apply Acrylic Latex Traffic Paint by brush, roller or airless spray. (1800—2400 PSI and .017 tip)</p> <p>Warning! Removal of old paint by sanding, scraping or other means may generate dust or fumes that contain lead. Exposure to lead dust or fumes may cause brain damage or other adverse affects, especially in children or pregnant women. Controlling exposure to lead or other hazardous substances requires the use of proper protective equipment, such as a properly fitted respirator (NIOSH approved) and proper containment and cleanup. For more information, call the National Lead Information Center at 1-800-424-LEAD (in US) or contact your local health authority.</p> <p>Mildew Remove before painting by washing with a solution of 1 part liquid bleach and 3 parts water. Apply the solution and scrub the mildewed area. Allow the solution to remain on the mildewed area for 10 minutes. Rinse thoroughly with water and allow the surface to dry prior to painting. Wear protective eyewear, waterproof gloves, and protective clothing. Quickly wash off any mixture that comes in contact with your skin. Do not add detergents or ammonia to the bleach water solution.</p>	<p style="text-align: center;"><u>Surface Preparation</u></p> <p>Masonry, Concrete, Cement, Block All new surfaces must be cured according to the supplier's recommendations usually about 30 days. Remove all form release and curing agents. Rough surfaces can be filled to provide a smooth surface. The newly cured surface should then be etched with muriatic acid as follows.</p> <ul style="list-style-type: none"> • Efflorescence (salts): Apply a solution of 1 part muriatic acid to 3 parts water, rinse well allow to dry. <p style="text-align: center;"><u>Cleanup Information</u></p> <p>Clean spills and spatters immediately with soap and warm water. Clean hands and tools immediately after use with soap and warm water. After cleaning, flush spray equipment with mineral spirits to prevent rusting of the equipment. Follow manufacturer's safety recommendations when using mineral sprits.</p>
--	--	---