

# Associated Paint, Inc.



## Dura-Grip.01 Driveway and Floor Coating Data Sheet

<u>Characteristics:</u>	<u>Surface Preparation</u>	<u>Surface Preparation</u>
<p>Dura-Grip is an extremely durable protective coating for concrete and asphalt surfaces. Dura-Grip goes on easily and dries to a medium luster finish that resists oil, water, algae, and mildew. When applied properly, Dura-Grip resists hot tire pick-up, peeling and flaking.</p> <p><b>Vehicle Type:</b> Acrylic</p> <p><b>FINISH:</b> medium Sheen</p> <p><b>RECOMMENDED USES:</b></p> <ul style="list-style-type: none"> <li>• Concrete</li> <li>• Garage Floors</li> <li>• Tennis Courts</li> <li>• Patio's</li> <li>• Asphalt Sur-faces</li> <li>• Factory Floors</li> </ul> <p><b>TINTING:</b> Dura-Grip may be tinted to a wide range of colors with universal colorants in addition to our, more popular, stock colors.</p> <p><b>THINNING:</b> Not recommended.</p> <p style="text-align: center;"><b><u>Specifications</u></b></p> <p><b>DRYING TIME, @ 77° F, 50% RH:</b> Temperature &amp; Humidity Dependent</p> <p><b>Touch:</b> 2 hours  <b>Light foot traffic:</b> 8 hours  <b>Heavy foot traffic:</b> 48 hours  <b>Vehicle traffic:</b> 72 hours  <b>Flash Point:</b> N/A</p> <p><b>VOC:</b> &lt;150 g/l</p> <p><b>Weight Solids:</b> 39.5% ± 2%  <b>Volume Solids:</b> 27.4% ± 2%  <b>Weight Per Gallon:</b> 10.1 Lbs</p> <p><b>COVERAGE:</b> Dura-Grip will cover up to 250—350 sq.ft per gallon @ 4.0 mils wet, 1.5 mils dry</p> <p><b>APPLICATION:</b> Apply Dura-Grip by brush, roller or airless spray. (1800—2400 PSI and .017 tip)</p>	<p><b>Warning!</b> Removal of old paint by sanding, scraping or other means may generate dust or fumes that contain lead. Exposure to lead dust or fumes may cause brain damage or other adverse affects, especially in children or pregnant women. Controlling exposure to lead or other hazardous substances requires the use of proper protective equipment, such as a properly fitted respirator (NIOSH approved) and proper containment and cleanup. For more information, call the National Lead Information Center at 1-800-424-LEAD (in US) or contact your local health authority.</p> <p><b>Previously Painted Surfaces</b> Surfaces must be clean and sound. Follow recommendations for new concrete. All glossy surfaces must be dulled by sanding. If in doubt of adhesion, try a test area by applying a coat of <b>Dura-Grip</b> and allowing to dry for 2 days. Press a piece of duct tape firmly over the coating. Pull up sharply. If the coating pulls from the surface, the Dura-Grip should not be used or apply Bond-Grip following the instructions. Repeat the same tape test in order to test adhesion before continuing. Dura-Grip should not be used over stains or coatings containing silicone or siloxane / silicates.</p> <p><b>Mildew</b> Remove before painting by washing with a solution of 1 part liquid bleach and 3 parts water. Apply the solution and scrub the mildewed area. Allow the solution to remain on the mildewed area for 10 minutes. Rinse thoroughly with water and allow the surface to dry prior to painting. Wear protective eyewear, waterproof gloves, and protective clothing. Quickly wash off any mixture that comes in contact with your skin. Do not add detergents or ammonia to the bleach water solution.</p>	<p><b>Masonry, Concrete, Cement, Block</b> All new surfaces must be cured according to the supplier's recommendations usually about 30 days. Remove all form release and curing agents. Rough surfaces can be filled to provide a smooth surface. The newly cured surface should then be etched with muriatic acid as follows. Remove grease &amp; oil with a good degreaser.</p> <p>For stubborn stains or heavy contamination pressure cleaning is recommended. Smooth troweled or slick concrete must be etched with a solution of 1 pint muriatic acid to 1 gallon of water. Apply to concrete and allow to remain until bubbling has stopped. Flush with water. The surface should feel like sandpaper. If not, repeat etching. Be sure to flush all acid residue from surface and allow to dry.</p> <p><b>New Asphalt</b> Allow to weather at least 6 months. Pressure wash and clean up and grease or oil with a good degreaser. Flush with clean water and allow to dry.</p> <ul style="list-style-type: none"> <li>• <b>Efflorescence (salts):</b> Apply a solution of 1 part muriatic acid to 3 parts water, rinse well allow to dry.</li> </ul> <p><b><u>Cleanup Information</u></b> Clean spills and spatters immediately with soap and warm water. Clean hands and tools immediately after use with soap and warm water. After cleaning, flush spray equipment with mineral spirits to prevent rusting of the equipment. Follow manufacturer's safety recommendations when using mineral spirits.</p> <p><b>Dura-Grip may become slippery when wet. A slip resistant additive is recommended for pedestrian areas.</b></p>