

# Associated Paint, Inc.



## 11-20H2O.01

### Wet-Look H2O Clear Sealer Data Sheet

<u>Characteristics:</u>	<u>Specifications</u>	<u>Surface Preparation</u>
<p><b>Wet-Look H2O</b> is a waterborne acrylic sealer that offers that glossy, wet look appearance. <b>Wet-Look H2O</b> goes on easily and dries to a clear, gloss finish that resists oil, grease, fuels, water, algae and mildew.</p> <p><b>Wet-Look H2O</b> will not yellow, peel or crack.</p> <p><b>Vehicle Type:</b> 100% Acrylic</p> <p><b>FINISH:</b> Gloss</p> <p><b>RECOMMENDED USES:</b></p> <ul style="list-style-type: none"> <li>• Concrete</li> <li>• Stamped Concrete</li> <li>• Masonry Surfaces</li> <li>• Chattahoochee or exposed aggregate</li> <li>• Decorative Stone</li> <li>• Brick Pavers</li> </ul> <p><b>TINTING:</b> None</p> <p><b>THINNING:</b> Not recommended.</p> <p><b>DRYING TIME, @ 77° F, 50% RH:</b> Temperature &amp; Humidity Dependent</p> <p><b>Touch:</b> 60 minutes <b>Recoat:</b> 4 hours Allow 72 hours dry time before heavy traffic.</p> <p><b>Flash Point:</b> N/A</p> <p><b>VOC:</b> &lt;250/ g/l</p> <p><b>Weight Solids:</b> 25 <b>Volume Solids:</b> 23.5 <b>Weight Per Gallon:</b> 8.6 Lbs</p> <p><b>COVERAGE:</b> <b>Wet-Look H2O</b> will cover up to 200 sq.ft per gallon @ 4.5 mils wet, 1.5 mils dry film thickness.</p>	<p><b>APPLICATION:</b> Apply <b>Wet-Look H2O</b> by brush, roller (short Nap Mohair) or low pressure airless spray.</p> <p>One coat is usually sufficient however if a second coat is desired, allow a minimum of 4 hours between coats.</p> <p><b><u>Surface Preparation</u></b></p> <p>All surfaces to be coated must be clean and free of moisture, efflorescence, dirt, grease, oil, chalk, mildew and any other foreign matter.</p> <ul style="list-style-type: none"> <li>• <b>Oils, Grease, Dirt:</b> Scrub with TSP, detergent and/or a degreaser, rinse well &amp; allow to dry.</li> <li>• <b>Mildew &amp; Algae:</b> Apply a solution of 1 part bleach to 3 parts water, rinse well and allow to dry.</li> <li>• <b>Efflorescence (salts):</b> Apply a solution of 1 part muriatic acid to 3 parts water, rinse well allow to dry.</li> </ul> <p><b>Sealed, painted or waxed surfaces:</b> To allow proper penetration of <b>Wet-Look H2O</b>, all sealers, paint, etc. should be removed prior to it's application. <b>Wet-Look H2O</b> is designed for use on uncoated surfaces or over itself, however good results may be obtained when used over similar water based acrylic type coatings/sealers. Before attempting to apply <b>Wet-Look H2O</b> over existing coatings check for adhesion and compatibility by coating a small test area. If lifting, wrinkling, excessive bubbling, slow drying, or other undesirable conditions occur, the previous coating must be completely removed.</p> <p><b>Brick Pavers:</b> Follow all instructions as noted above, paying particular attention to efflorescence. Make certain joints are filled with sand allowing minimum 1/4" recess between top of sand joint &amp; top of brick.</p>	<p><b>Steel Floated Concrete:</b> To allow proper penetration of <b>Wet-Look</b>, concrete that is shiny smooth should be etched with 1 part muriatic acid to 3 parts water. Rinse well and allow to dry thoroughly.</p> <p><b>New Concrete:</b> Allow new concrete to cure a minimum of 28 days. Acid etch with a solution of 1 part muriatic acid to 3 parts water to remove efflorescence and provide a sound paintable surface. Rinse well and allow to dry thoroughly.</p> <p><b>Important Do's &amp; Don'ts</b></p> <ul style="list-style-type: none"> <li>• Surface <b>must be</b> dry for 24 hours before application!</li> <li>• Do not apply when temperature is below 50°F or above 90°F.</li> <li>• Do not apply if rain or heavy dew is threatening.</li> <li>• Do not thin.</li> <li>• Avoid heavy buildup and overlapping of sealer.</li> <li>• One coat is usually sufficient. However, if a second coat is desired, allow 4 hours between coats.</li> </ul> <p><b><u>Cleanup Information</u></b></p> <p>Clean spills and spatters immediately with soap and warm water. Clean hands and tools immediately after use with soap and warm water. After cleaning, flush spray equipment with mineral spirits to prevent rusting of the equipment. Follow manufacturer's safety recommendations when using mineral spirits</p> <p><b>Non-Skid:</b> Sealed surfaces, particularly those sealed with High Solids sealers, may become slippery when wet. A Non-Skid additive product may be added to help reduce slipping.</p>